











UNIQUE GLO

PO Box 404, Manteno, IL. 60950 (815)545-7650
 E-mail: ebrooks2000@hotmail.com or r.allman@att.net



PS Series Sulfide based Photoluminescent Pigment List.

Model	Size (um)	Afterglow Intensity (mcd/m ²)					Glow time	Glowing color (Night)	Appearance (Daytime)
		1min	5min	30min	60min				
PLS=05YG	10~28	500	89	10	4	5hr	 yellow-green	 Light-yellow	
PLS-01RR	20~50	400	50	2.5	1	>1hr	 red	 red	
PLS-01RO	20~50	400	50	2.5	1		 orange-red	 Orange	
PLW-06GW	15~45	900	300	54		>6hr	 White	 White	
PLS-06GO	10~45	460	60	3.2	1.1	>6hr	 Orange	 White	

Note:

Luminance test conditions: D65 standard light source at 1000LX luminous flux density for 10min of excitation